

## Centro Tessile Serico Sostenibile Srl

via Castelnuovo, 3 - 22100 Como Italia Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154

P. IVA - C.F. 003900470133 Capitale sociale euro 600000,00 iv mailbox@textilecomo.com www.textilecomo.com





LAB N° 0045 L

Test Report No.: 2400865-002

**Date Test Report** 13-feb-24

Acceptance: 2400865

Arrival date sample 08-feb-24

Start date test 08-feb-24

End date test

References:

Rheinauenstrasse 8 79415 Bad Bellinen Germany 09-feb-24

> C.a. Mario Ghioldi

Customer Code 08796-1

SILENT GLISS FABRICS & COMPONENTS GmbH

Phone:

Dear:

Sampling Mode: Sampling by Customer \*

**MULTICOLOUR NATURA** [C] Item: [C] Declared Composition: 100% Polvester FR [C] End use: furnishing

fabric [C] Typology: no requested Return:

## **Test Results**

Method U.M. Test **UNI EN ISO 6330:2022 25165 WASHING TREATMENTS** 

Start date test 19/01/2024 End date test 22/01/2024

Instrument: WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 CLS

Typology of washing machine used: Type A Programme of washing: 3G - gentle agitation

Test Temperature: 30°C

Drying procedure: type C - Flat dry

Detergent used: ECE (ref.A) without optical brightener - Sodium Perborated- TAED

Total air-dry- mass (specimens and ballast): 2,0 kg Type of ballast used: Type III (polyester) Number of washings performed: 01

THE SAMPLE, TREATED AS ABOVE DESCRIBED, HAS BEEN SUBMITTED TO NEXT TEST of CURTAINS AND DRAPES: IGNITABILITY OF VERTICALLY ORIENTED SPECIMENS.

UNI FN 1101:2006

15386 CURTAINS AND DRAPES: **IGNITABILITY OF VERTICALLY ORIENTED** 

**SPECIMENS** 

Start date test 23/01/2024

25/01/2024 End date test

Instrument: Rhoburn Tester

Pretreatment carried out 1 washing at 30°C Conditioning of sample  $24 \text{ h a } 20 \pm 2 \,^{\circ}\text{C}, 65 \pm 5 \,^{\circ}\text{w.r.}$ Testing temperature and r.h. 18°C, 50% r.h. Type of gas used: propane Type of ignition used: edge ignition

# (\*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



## Centro Tessile Serico Sostenibile Srl

Capitale sociale euro 600000,00 iv

mailbox@textilecomo.com

via Castelnuovo, 3 - 22100 Como Italia Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154 P. IVA - C.F. 003900470133





LAB N° 0045 L

Test Report No.:

2400865-002

UNI EN 13772:2011

Test Method U.M. Result

MEAN IGNITION TIME

SAMPLE DOES NOT BURN AT 20 s OF APPLICATION TIME OF THE FLAME

SAMPLE DOES NOT BURN AT 20 s OF APPLICATION TIME OF THE FLAME

Deviations from the methodnoneAnnex n.1F

Details of the test results related to each specimen can be seen in the annex of this test report.

25165 WASHING TREATMENTS UNI EN ISO 6330:2022

 Start date test
 19/01/2024

 End date test
 23/01/2024

Instrument: WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 CLS

Typology of washing machine used: Type A Programme of washing: 3G - gentle agitation

Test Temperature: 30°C

Drying procedure: type C - Flat dry

Detergent used: ECE (ref.A) without optical brightener - Sodium Perborated- TAED

Total air-dry- mass (specimens and ballast): 2,0 kg Type of ballast used: Type III (polyester) Number of washings performed: 12

THE SAMPLE, TREATED AS ABOVE DESCRIBED, HAS BEEN SUBMITTED TO NEXT TEST of BURNING BEHAVIOUR - CURTAINS AND DRAPES - Measurement of flame spread of vertically oriented specimens with large ignition source.

15676 BURNING BEHAVIOUR - CURTAINS

AND DRAPES - Measurement of flame spread of vertically oriented specimens with

large ignition source

 Start date test
 25/01/2024

 End date test
 25/01/2024

Instrument: Rhoburn Tester

Conditioning of sample		24 h a 20 ± 2 °C, 65 ± 5 % u.r.
Testing temperature and r.h.		18°C, 50% r.h.
TEST ON SAMPLE IN ITS ORIGINAL STATE:		
- severing of marker threads	-	NO
Evidence of flaming debris	-	NO
TEST ON REFURBISHED SAMPLE:		
- severing of marker threads	-	NO
Evidence of flaming debris	-	NO
Deviations from the method		none
Annex n.		2F
Details of the test results related to each specimen can be seen in the annex of this test report.		

<sup>(\*) =</sup> The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

<sup>[</sup>C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Test Report No.:

## Centro Tessile Serico Sostenibile Srl

Capitale sociale euro 600000,00 iv

2400865-002

mailbox@textilecomo.com

via Castelnuovo, 3 - 22100 Como Italia Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154 P. IVA - C.F. 003900470133





LAB N° 0045 L

Test Method U.M. Result

15986 TEXTILES AND TEXTILE PRODUCTS - EN 13773:2004 BURNING BEHAVIOUR - CURTAINS AND DRAPES - CLASSIFICATION SCHEME CLASS 1

The fabric tested according to standards

UNI EN 1101: 2006 "Textiles and textile products. Burning behaviour. Curtains and drapes. Detailed procedure to determine the ignitability of vertically oriented specimens (small flame)" and

UNI EN 13772: 2011 "Textiles and textile products. Burning behaviour. Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source"

MEETS THE REQUIREMENTS OF CLASS 1 according to the UNI EN 13773: 2004"Textiles and textile products - Burning behavior - Curtains and drapes - Classification scheme"

The Laboratory Manager

Fausto Albonico

**END OF REPORT** 

(\*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.