

Centro Tessile Serico Sostenibile Srl

www.textilecomo.com

via Castelnuovo, 3 - 22100 Como Italia Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154 P. IVA - C.F. 003900470133 Capitale sociale euro 600000,00 iv





LAB N° 0045 L

Test Report No.: 2400865-003

Date Test Report 13-feb-24

Acceptance: 2400865 Arrival date sample 08-feb-24

Start date test 08-feb-24 End date test

References:

[C] Item:

Sampling Mode:

12-feb-24

Sampling by Customer *

[C] Declared Composition: [C] End use:

[C] Typology: Return:

Customer Code 08796-1

Dear:

SILENT GLISS FABRICS & COMPONENTS GmbH

Rheinauenstrasse 8

79415 Bad Bellinen Germany

C.a. Mario Ghioldi

Phone:

MULTICOLOUR PANAMA 100% Polyester FR

furnishing fabric

no requested

Test Results

Test		Method	U.M.	Result
15246 FLAMMABILITY REQUIREMENTS FOR FABRICS CURTAINS, DRAPES AND WINDOW BLINDS (type B)				
Start date test	23/01/2024			
End date test	25/01/2024			
Instrument: Rhoburn	Tester			
Pretreatment carried out				none
Test method used				ref. EN 15025
Tested sample surface:				face
Dimension of specimens	s:		mm	160x200
Type of gas used:				propane
Type of ignition used:				surface ignition
Time of application of fl	ame:		S	15
Conditioning of sample				24 h at 20 ± 2 °C, 65 ± 5 % r.h.
Testing temperature and r.h.				18°C, 50% r.h.
Number of tests specimens				6
TEST RESULT				SAMPLE MEETS THE BS 5867- 2:2008 Type B REQUIREMENTS
Deviations from the me	thod			none
Annex n.				1F
Details of the test results r	elated to each specimen	can be seen in the annex of this test report		

^{(*) =} The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[[]C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl

via Castelnuovo, 3 - 22100 Como Italia Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154





LAB N° 0045 L

P. IVA - C.F. 003900470133 Capitale sociale euro 600000,00 iv mailbox@textilecomo.com

Test Report No.:

2400865-003

Method U.M. Result Test

* 25165 WASHING TREATMENTS UNI EN ISO 10528:1997

Start date test 19/01/2024 End date test 23/01/2024

Instrument: WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 CLS

Typology of washing machine used: Type A Programme of washing: 3G - gentle agitation Test Temperature: 30°C

Drying procedure: type C - Flat dry

Detergent used: ECE (ref.A) without optical brightener - Sodium Perborated- TAED

Total air-dry- mass (specimens and ballast): 2,0 kg Type of ballast used: Type III (polyester) Number of washings performed: 12

THE SAMPLE, TREATED AS ABOVE DESCRIBED, HAS BEEN SUBMITTED TO NEXT TEST OF FLAMMABILITY REQUIREMENTS FOR FABRICS CURTAINS, DRAPES AND WINDOW BLINDS (type

15246 FLAMMABILITY REQUIREMENTS FOR BS 5867-2:2008

FABRICS CURTAINS, DRAPES AND WINDOW

BLINDS (type B)

Start date test 23/01/2024 End date test 25/01/2024

Instrument: Rhoburn Tester

Pretreatment carried out		12 washing at 30°C
Test method used		ref. EN 15025
Tested sample surface:		face
Dimension of specimens:	mm	160x200
Type of gas used:		propane
Type of ignition used:		surface ignition
Time of application of flame:	S	15
Conditioning of sample		24 h at 20 ± 2 °C, 65 ± 5 % r.h.
Testing temperature and r.h.		18°C, 50% r.h.
Number of tests specimens		6
TEST RESULT		SAMPLE MEETS THE BS 5867- 2:2008 Type B REQUIREMENTS
Deviations from the method		none
Annex n.		1F
Details of the test results related to each specimen can be seen in the annex of this test report.		

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.

^{(*) =} The tests marked in this way are not accredited by Accredia

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.



Centro Tessile Serico Sostenibile Srl

Capitale sociale euro 600000,00 iv

mailbox@textilecomo.com

via Castelnuovo, 3 - 22100 Como Italia Pho +39 031 3312111/120 Fax: +39 0313312149 Amministrazione/Contabilità +39 031 3312102-154 P. IVA - C.F. 003900470133





LAB N° 0045 L

Test Report No.:	2400865-003			
Test	Method		U.M.	Result
				The Laboratory Manager Fausto Albonico
		END OF REPORT		

The Results contained in this Report refer only to the sample as received and to the objects tested and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

^{(*) =} The tests marked in this way are not accredited by Accredia

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.